

FLEXIBLE POLYOLEFIN THIN WALL 3 : 1 Shrink Ratio

UL/ CSA RECOGNIZED 125°C 600V (VW-1)

 **RoHS Compliant**

TYPICAL FEATURES

- | | |
|---|---|
| <p>1) SUMITUBE® B2(3X) is a very flexible, flame-retarded, heat-shrinkable polyolefin tubing. B2(3X) is overexpanded to have a recovery ratio of 3 to 1, as opposed to the normal 2 to 1 recovery. B2(3X) is recognized by UL under Subject 224 as 125°C 600V with a VW-1 rating.</p> <p>2) SUMITUBE® B2(3X) meets the material and functional properties of AMS-DTL-23053/5, Classes 1 & 3, with exception to dimensions.</p> <p>3) B2(3X) has a low recovery temperature of 90°C.</p> | <p>4) B2(3X) has an operating temperature range of -55°C to +135°C with up to 200°C for short duration.</p> <p>5) B2(3X) is recommended for use in general purpose applications for protection of components in light wire harness assemblies. It can be used where oversized sub-components prevent the use of a standard heat shrinkable tubing. It can also provide the user with better economies, as one size tubing can often replace 2 standard 2:1 expanded tubing sizes, thereby reducing inventories.</p> |
|---|---|

STANDARD SIZES

NOMINAL SIZE (MM)	INSIDE DIAMETER AS SUPPLIED (MIN)		INSIDE DIAMETER AFTER RECOVERY (MAX)		WALL THICKNESS AFTER RECOVERY (NOM)	
	INCH	(MM)	INCH	(MM)	INCH	(MM)
	1.5/0.5	.060	1.5	.020	0.5	.020
3/1	.120	3.0	.040	1.0	.024	.60
6/2	.240	6.0	.080	2.0	.028	.70
9/3	.360	9.0	.120	3.0	.031	.80
12/4	.472	12.0	.160	4.0	.033	.85
18/6	.720	18.0	.240	6.0	.039	1.0
24/8	.945	24.0	.315	8.0	.048	1.2
40/13	1.575	40.0	.515	13.0	.050	1.25
50/17	2.000	50.0	.670	17.0	.059	1.50
75/25	3.000	75.0	1.000	25.0	.065	1.65
102/34	4.000	102.0	1.330	34.0	.071	1.80

Standard Colors: Black, White, Red, Yellow, Blue
Standard Package: 4 feet (4') or Spooled (S) (continuous lengths)
How to Order: (Type of material) (Size) (Color) (Packaging)
Example: B2(3X) 6/2 Black S

B2 (3X) SPECIFICATION VALUES

PROPERTY (UNITS)	TEST METHOD	REQUIREMENT
Physical: Tensile strength (psi) Elongation (%) Specific gravity Low temperature flex (-55 ⁰ C) Heat shock Heat resistance (175 ⁰ C, 168 hrs.) Elongation (%) Secant modulus (psi) Longitudinal change (%)	ASTM D638 ASTM D638 ASTM D792 AMS-DTL-23053 AMS-DTL-23053 ASTM D638 ASTM D882 AMS-DTL-23053	1500 min. 200 min. 1.35 max. no cracking no cracking 100 min. 2.5 x 10 ⁴ max. +5, -15
Electrical: Dielectric strength (volts/mil) Volume resistivity (ohm-cm)	ASTM D876 ASTM D876	500 min. 1.0 X 10 ¹⁴ min.
Chemical: Corrosion Water absorption (%) Fluid resistance (23 ⁰ C, 24 hrs.) Tensile strength (psi) Flammability Shrink temperature, nominal	AMS-DTL-23053 ASTM D 570 AMS-DTL-23053 UL 224 VW-1	no corrosion 0.5 max. 1000 min. pass 90 ⁰ C

Specification reference: UL 224 125⁰C, 600V, VW-1
 File E48762 YDPU2, Cat. No. B2(3X) or 826 suffix (3X)
 CSA C22.2 No. 198.1-98



915 Armorlite Drive
 San Marcos, CA 92069

Telephone: (800) 758-3515
 FAX: (800) 758-3517

Rev. 2/21/05